

LAPOX[®] ART-24 | AH-326



Technical Data Sheet | Polymers Business

Ambient cure colourless epoxy gel coat

Lapox ART-24	100	pbw
Lapox AH-326	15	pbw

Description

Lapox ART-24 is a white coloured modified epoxy resins for gel coat applications. It can be suitably coloured for aesthetic look. This resin is a mineral filled system and has tendency to settle. Stir it properly before use. Lapox AH-326 is a hardener suitable to cure gel coat resins at ambient temperature. They both are thixotropic in nature and provides slightly white resilient, machinable surface with good edge strength. Soft brush of medium length bristles are recommended to apply this gel coat.

Typical specifications

Lapox ART-21

Properties	Unit	Test method	Values
Appearance	-	Visual	Hazy, white liquid
Viscosity at 25°C	m Pas	ASTM D2196	25,000 - 45,000

Lapox AH-326

Properties	Unit	Test method	Values
Appearance	-	Visual	Clear, yellow liquid
Viscosity at 25°C	m Pas	ASTM D2196	3,400 - 5,000
Density at 25°C	g/cm ³	ISO 1183	1.05 - 1.1

Processing properties

Properties	Unit	Test method	Values
Mixing ratio (by weight)	pbw	-	100 : 15
Pot life at 25°C	Minutes	ASTM D2471	15 - 30
Demoulding at 25°C	Hours	-	4 - 6
Curing time	Hours / °C	-	4 / 80 °C

Typical properties of neat cured system

Curing schedule: 4 hours / 80 °C
Determined on standard test specimen at 25°C

Properties	Unit	Test method	Values
Tensile strength	MPa	ISO 527	60 - 70
Elongation at break	%	ISO 527	2 - 4
Elastic modulus in tension	GPa	ISO 527	3.0 - 3.3
Flexural strength	MPa	ISO 178	120 - 130
Flexural elongation at break	%	ISO 178	4 - 8
Elastic modulus in flexural	GPa	ISO 178	3.0 - 3.3

Packaging

Lapox ART-24 is available in 30 kg, 110 kg and 240 kg carboys. Lapox AH-326 is available in 1 kg HDPE bottles. Other packing may be considered on request.

LAPOX[®] ART-24 | AH-326

Technical Data Sheet | Polymers Business



Storage and handling

Lapox ART-24 and Lapox AH-326 have shelf-life of 1 year if stored in their original sealed containers. Hardener is sensitive to moisture. Container must be closed properly immediately after use. Both resin and hardener may cause irritation to sensitive skins. If contact does occur then it should be washed off immediately with soap and warm water, consult doctor immediately. Please refer to the Safety Data Sheet (SDS) for detailed instructions on storage and handling.

Safety

Wear personal protective equipment (PPE). Avoid contact with the eyes and skin. In case of direct contact and irritation, the resin should be washed off immediately with soap and warm water. Avoid breathing vapours, mist or gas. Please refer to the SDS for detailed safety instructions.

Spills and disposal

In case of spills, sweep up and shovel the spilled material. Keep spilled material in suitable, closed containers for disposal. Soak up with an absorbent such as clay, sand or other suitable material. Flush area with water to remove trace residue. Do not allow the product to reach the sewage system. Waste must be disposed of in accordance with federal, state or local regulations, as applicable.

Contact

E-mail: polymers@atul.co.in
Website: www.atul.co.in

Note

Lapox[®] is a registered trademark of Atul Ltd.

Manufacturing site

Atul 396 020, Gujarat, India
Telephone: (+91 2632) 230000 | 233261
E-mail: contact@atul.co.in

Disclaimer: The information contained herein is for information purposes only. While enough care is taken in disclosing the information, users of this information are advised to cross-check the same depending upon use | application. Atul Ltd does not give any assurance or warranty or guarantee in regard to the accuracy or completeness of the information and no claim or liability will be accepted or entertained in regard thereto. Atul Ltd makes no warranty of any kind, expressed or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose or performance or usage of trade.